

WOODguard TC™

Top Coat - Product Data Sheet

Product Description and Use:

- Water-based, acrylic latex resin
- Extends the life of WOODguard and WOODguard ITF coating
- For use on all interior or exterior wood surfaces except floors
- Clear satin or gloss formulas
- Washable, non-yellowing
- VOC-compliant
- Quick-drying

Features:

- VOC-compliant in all 50 states
- Provides a breathable finish to allow moisture to escape and evaporate
- Recommended as a top coat over WOODguard® and WOODguard ITF™. Covers 300 to 450 square feet/gallon.
- Wait until dry to the touch to apply second coat (if desired)
- Gives a gloss or satin finish
- Can be applied over raw wood with no primer
- WOODguard can be applied over WOODguard TC for retreatment as needed.

Technical Data:

Appearance:	Milky Liquid
Flash Point:	Not applicable, water based
Viscosity:	100 – 400 CPS @ 20°C
Pour Point:	Above 32°F
Specific gravity:	8.64 –8.831 lbs/gal
Corrosivity:	none
Storage Stability:	Pending
	DO NOT FREEZE
pH:	8.7 – 9.1

™WOODguard TC and WOODguard ITF are trademarks of IBC Manufacturing Company.
®WOODguard is a registered trademark of IBC Manufacturing Company.

Application:

Stir well before and occasionally during use. **Do not over apply.** For best results do not apply below 50° F, during rain or excessive humidity.

The preferred application method is an airless sprayer. When spraying, you will need to back brush or roll the sprayed surfaces immediately to maintain a sheer, even, translucent appearance. Because WOODguard TC dries very quickly, the spray application option may be a two-person job - one with a sprayer and one with a brush or low-nap roller. Application by brush is acceptable. Regardless of application method, maintain a wet edge to prevent lap marks. Coverage: Expect approximately 300 - 450 square feet per gallon on smooth, dry wood when proper application techniques are employed. On rough wood, coverage may be considerably less. On second coat, coverage will generally be more.

When applying WOODguard TC over WOODguard ITF, allow 2 - 3 days before applying WOODguard TC. When applying over WOODguard, allow 2 - 3 weeks before applying WOODguard TC. Cure time is dependent on temperature and humidity and a longer time may be required when conditions are cool and/or moist.

Warranty and Limitation of Damages:

Seller warrants to those persons lawfully acquiring title to this product that at the time of the first sale of this product by seller this product conformed to its chemical description and that it was reasonably fit for the purposes stated on the product label when used both in accordance with the Directions for Use appearing on the product label and under normal conditions of use. Buyers and users of this product assume the risk of all loss or damage from use or handling of this product that results from their failure to read and comply with the Directions for Use of this product, which appear on the product label. SELLER MAKES NO OTHER EXPRESS OR IMPLIED WARRANTY, INCLUDING ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS OR OF MERCHANTABILITY, AND NO AGENT OF SELLER IS AUTHORIZED TO DO SO. Unless expressly prohibited by state law, the liability of seller for any breach of warranty shall not exceed the purchase price of the product as to which a claim is made.

ISK Biocides, Inc.

416 East Brooks Rd.
Memphis, TN 38109
Ph: 1-800-238-2523
Fax: 901-344-5388